



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08F 297/08, 2/42, 4/642, 4/654	A1	(11) International Publication Number: WO 96/11218 (43) International Publication Date: 18 April 1996 (18.04.96)
(21) International Application Number: PCT/EP95/03896 (22) International Filing Date: 2 October 1995 (02.10.95) (30) Priority Data: MI94A002028 5 October 1994 (05.10.94) IT (71) Applicant: MONTELL TECHNOLOGY COMPANY BV [NL/NL]; Hoeksteen 66, NL-2132 MS Hoofddorp (NL). (72) Inventors: COLLINA, Gianni; Via Calzavecchio, 38, I-40033 Casalecchio di Reno (IT). DALL'OCCO, Tiziano; Via F. Neri, 8, I-44100 Ferrara (IT). GALIMBERTI, Maurizio; Via Vertoiba, 4, I-20137 Milano (IT). ALBIZZATI, Enrico; Via Roma, 64, I-28041 Arona (IT). NORISTI, Luciano; Via Comitato di Liberazione, 19, I-44100 Ferrara (IT). (74) Agent: ZANOLI, Enrico; Spherilene S.p.A., Via Taramelli, 26, I-20124 Milano (IT).		(81) Designated States: AU, BG, BR, CA, CN, CZ, FI, HU, JP, KR, MX, NO, PL, RO, RU, SK, UA, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>

(54) Title: PROCESS FOR THE (CO)POLYMERIZATION OF OLEFINS**(57) Abstract**

Multistage process for the polymerization of one or more olefins of the formula $\text{CH}_2=\text{CHR}$, in which R is hydrogen or an alkyl, cycloalkyl or aryl group having from 1 to 10 carbon atoms, comprising: (A) a first stage of polymerization, in which a first olefin polymer is prepared in the presence of titanium catalyst or vanadium catalyst; (B) a treatment stage in which the catalyst used previously is deactivated and in which a metallocene compound is supported on the olefin polymer produced in stage (A); and (C) a second stage of polymerization in which one or more olefins are polymerized in the presence of the product obtained from stage (B).

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

Title**"PROCESS FOR THE (CO)POLYMERIZATION OF OLEFINS"**

The present invention relates to a process with several stages for the polymerization of olefins $\text{CH}_2=\text{CHR}$, where R is hydrogen or an alkyl, cycloalkyl or aryl radical with 1-10 carbon atoms, carried out in two or more reactors. In at least one reactor, one or more of the said olefins are polymerized in the presence of a catalyst comprising the product of the reaction of an alkyl-Al compound with a compound of Ti and/or V supported on a magnesium halide in active form, obtaining an olefin polymer. In at least one other reactor, upon deactivation of the catalytic system operating in the first reactor, one or more of the said olefins $\text{CH}_2=\text{CHR}$ are polymerized in the presence of the product obtained by bringing the said olefin polymer into contact with a compound of a transition metal M containing at least one M- π bond, obtaining new polymer compositions directly from the reactors.

Multistage processes for the polymerization of olefins, carried out in two or more reactors, are known from the patent literature and are of particular interest in industrial practice. The possibility of independently varying, in any reactors, process parameters such as temperature, pressure, type and concentration of monomers, concentration of hydrogen or other molecular weight regulator, provides much greater flexibility in controlling the composition and properties of the end product with single-stage processes.

Multistage processes are generally carried out using the same catalyst in the various stages/reactors: the product

obtained in one reactor is discharged and sent directly to the next stage/reactor without altering the nature of the catalyst.

Processes in several stages find application for example in the preparation of olefin (co)polymers with broad molecular weight distribution (MWD), by producing polymer species with different molecular weight in the various reactors. The molecular weight in each reactor, and therefore the range of the MWD of the final product, is generally controlled by using different concentrations of a molecular weight regulator, which is preferably hydrogen. Multistage processes are also used in the preparation of high-impact propylene copolymers by sequential polymerization of propylene and mixtures of propylene with ethylene. In a first stage, propylene is homopolymerized or copolymerized with smaller proportions of ethylene and/or olefins having 4-10 carbon atoms, obtaining a stereoregular polymer; in a second stage, mixtures of ethylene and propylene are polymerized in the presence of the polymer including the catalyst that is obtained in the first stage, obtaining polypropylene compositions having improved impact strength.

Processes of this type are described, for example, in USP 4,521,566. In said patent, polypropylene compositions having high impact strength are prepared in a multistage process which comprises at least one stage of homopolymerization of propylene and at least one stage of polymerization of ethylene/propylene mixtures in the presence, in both stages, of a catalyst comprising a compound of titanium supported on a magnesium halide in active form.

European Patent Application EP-A-433989 describes a process for preparing polypropylene composition containing from 20 to 99% by weight of a crystalline (co)polymer, containing at least

95% by weight of propylene units, and from 1 to 80% by weight of a noncrystalline ethylene/propylene copolymer, containing from 20 to 90% by weight of ethylene units. The process is carried out in 2 stages: in a first stage, carried out in liquid propylene, the crystalline propylene (co)polymer is produced, and in a second stage, carried out in hydrocarbon solvent, the noncrystalline ethylene/propylene copolymer is produced. The same catalyst, consisting of a chiral metallocene and an aluminoxane, is used in both stages.

European Patent Application EP-A-433990 describes a process in two stages for the preparation of propylene-based polymer composition similar to those described in EP-A-433989, in which the crystalline propylene (co)polymer is produced in the first stage by polymerization in liquid propylene, and the noncrystalline ethylene/propylene copolymer is produced in the second stage by gas-phase polymerization. Also in this case, the same catalyst, consisting of a chiral metallocene and an aluminoxane is used in both reactors.

German Patent Application DE 4130429 describes a multistage process for the production of block copolymers, effected entirely in the gas phase. In a first stage there is production of a matrix consisting of a homo or copolymer of propylene in a quantity of between 45 and 95% by weight based on the total product; in a second stage, carried out in the presence of the polypropylene matrix previously produced and of the catalyst used therein, an ethylene/ α -olefin copolymer is prepared, containing from 0.1 to 79.9% by weight of ethylene units, in a quantity of between 5 and 55% by weight based on the total product. In both stages, polymerization is carried out in the gas phase using the same metallocene catalyst.

The processes of the state of the art have various limitations, one of which derives from the fact that the same catalyst is used in the different process stages and therefore the characteristics of the products obtained in the individual stages are not always optimum. For example, in the case of heterophase copolymers prepared in multistage processes using titanium catalysts, the properties of the rubbery copolymer produced in the second stage are poor. In fact, it is known that titanium catalysts produce ethylene/propylene copolymers containing relatively long sequences of the same monomer unit and consequently the elastomeric properties of the product are poor .

It has now been found a multistage process by which it is possible to produce a wide range of olefin polymer compositions, working with different catalytic systems in the various stages. In particular, the process of the invention comprises a first stage in which, in the presence of titanium catalysts or vanadium catalysts, an olefinic polymer is prepared, and a second stage in which the catalyst used in the first stage is deactivated, and a third stage in which, in the presence of the said olefin polymer and of a compound of a transition metal M selected from Ti, Zr, V, or Hf containing at least one M- π bond and/or of their reaction products, one or more olefins are polymerized, said olefins being equal to or different from those polymerized in the first stage.

The process of the invention is characterized in that it comprises:

- (A) a first stage of polymerization in which one or more of said olefins $\text{CH}_2=\text{CHR}$ are polymerized, in one or more reactors, in the presence of a catalyst comprising the product of reaction between an alkyl-Al compound and a solid

component comprising a compound of a transition metal M^I selected from Ti and V, not containing M- π bonds, a halide of Mg in active form, to produce an olefin homo or copolymer;

- (B) a treatment stage in which the product obtained in the first stage of polymerization (A) is, in any order whatever:
- (a) contacted with a compound capable of deactivating the catalyst present in the said stage (A); and
 - (b) contacted with a compound of a transition metal M selected from Ti, Zr, V, or Hf containing at least one M- π bond and optionally with an alkyl-Al compound;
- (C) a second stage of polymerization in which one or more of said olefins are polymerized, in one or more reactors, in the presence of the product obtained in said treatment stage (B).

In one of the preferred embodiment, the olefin homo- or copolymer produced in the first stage of polymerization (A) has porosity, expressed as percentage of voids, greater than 5%, preferably greater than 10%, more preferably greater than 15%.

Preferably, the polymers produced in the first stage of polymerization (A) are characterized by the fact that they have macroporosity. In general, more than 40% of the porosity of the said polymers is due to pores with diameter greater than 10000 Å.

The porosity, expressed as percentage of voids, and the distribution of pore radius are determined by the mercury method described hereinafter.

When a rubbery copolymer is produced in stage (C), the porosity of the polymer produced in the first stage of

polymerization (A) makes it possible to work in the gas phase without particular problems.

The amount of polymer produced in the first stage of polymerization (A) is generally greater than 1000 g/g of solid component, preferably greater than 2000 g/g, more preferably greater than 3000 g/g.

The amount of polymer produced in polymerization stage (A) is preferably between 10 and 90% by weight relative to the total amount of polymer produced in stages (A) and (C) and more preferably is between 20 and 80%.

The catalyst used in the first stage of polymerization (A) comprises the product of the reaction between:

- (i) a solid component comprising a compound of a transition metal M^I selected from Ti and V and not containing $M^I-\pi$ bonds, supported on a magnesium halide in active form. The solid component can also comprise an electron-donor compound (internal donor). As a rule the internal donor is used when the solid component is used for preparing catalysts for the stereospecific polymerization of propylene, 1-butene and similar α -olefins, where a high stereospecificity is necessary to obtain polymers with an isotactic index higher than 90;
- (ii) an alkyl-Al compound and optionally an electron-donor compound (external donor).

When stereoregular polymers are produced in the first stage of polymerization (I), for example polymers of propylene with high isotacticity index, the external donor is used for imparting the necessary stereospecificity to the catalyst. However, when diethers of the type described in Patent EP-A-361493 are used as internal donors, the stereospecificity of the catalyst

is sufficiently high in itself and the external donor is not necessary.

The halides of magnesium, preferably $MgCl_2$, in active form used as support for Ziegler-Natta catalysts, are widely known from the patent literature. Patents USP 4,298,718 and USP 4,495,338 first described the use of these compounds in Ziegler-Natta catalysis. It is known from these patents that the halides of magnesium in active form used as support or co-support in components of catalysts for the polymerization of olefins are characterized by X-ray spectra in which the most intense diffraction line that appears in the spectrum of the non-active halide is diminished in intensity and is replaced by a halo whose maximum intensity is shifted towards lower angles compared with that of the most intense line.

The compound of the transition metal M^I is selected preferably from the group consisting of: halides of titanium, halogen-alcoholates of titanium, VCl_3 , VCl_4 , $VOCl_3$, halogen-alcoholates of vanadium.

Among the titanium compounds, the preferred are $TiCl_4$, $TiCl_3$ and the halogen-alcoholates of formula $Ti(OR^I)_mX_n$ in which R^I is a hydrocarbon radical with 1-12 carbon atoms or a $-COR^I$ group, X is a halogen and $(m+n)$ is the valence of titanium.

The catalytic component (i) is advantageously used in the form of spherical particles with mean diameter between about 10 and 150 μm . Suitable methods for the preparation of said components in spherical form are described for example in Patents EP-A-395083, EP-A-553805, EP-A-553806, whose description relating to the method of preparation and to the characteristics of the products is herein incorporated for reference.




Examples of internal donor compounds are ethers, esters, in particular esters of polycarboxylic acids, amines, ketones and 1,3-diethers of the type described in Patents EP-A-361493, EP-A-361494, EP-A-362705 and EP-A-451645.

The alkyl-Al compound (ii) is generally selected from the trialkyl aluminium compounds such as for example triethyl-Al, triisobutyl-Al, tri-n-butyl-Al, tri-n-hexyl-Al, tri-n-octyl-Al. It is also possible to use mixtures of trialkyl-Al's with alkyl-Al halides, alkyl-Al hydrides or alkyl-Al sesquichlorides such as AlEt_2Cl and $\text{Al}_2\text{Et}_3\text{Cl}_3$.


The external donor can be the same as or can be different from the internal donor. When the internal donor is an ester of a polycarboxylic acid, such as a phthalate, the external donor is preferably selected from silicon compounds of formula $\text{R}_1\text{R}_2\text{Si}(\text{OR})_2$, where R_1 and R_2 are alkyl, cycloalkyl or aryl radicals with 1-18 carbon atoms. Examples of such silanes are methylcyclohexyldimethoxysilane, diphenyldimethoxysilane, methyl-t-butyldimethoxysilane, dicyclopentyldimethoxysilane.

The compounds of the transition metal M used in treatment stage (b) are selected from the compounds of Ti, V, Zr and Hf containing at least one M- π bond. Preferably, said compounds contain at least one ligand L, having a mono- or polycyclic structure containing conjugated π electrons, coordinated on the metal M.

Said compound of Ti, V, Zr or Hf is preferably selected from components having the following structure:



in which M is Ti, V, Zr or Hf; Cp^{I} and Cp^{II} , equal or different, are cyclopentadienyl groups, or substituted cyclopentadienyl groups; two or more substituents on said cyclopentadienyl groups can form one or more rings having from 4 to 6 carbon atoms; R^1 , R^2 and R^3 , equal or different, are atoms of hydrogen, halogen, an alkyl or alkoxy group with 1-20 carbon atoms, aryl, alkylaryl or arylalkyl with 6-20 carbon atoms, an acyloxy group with 1-20 carbon atoms, an allyl group, a substituent containing a silicon atom; A is an alkenyl bridge or one with structure selected from:



$-\text{Ge}-$, $-\text{Sn}-$, $-\text{O}-$, $-\text{S}-$, $=\text{SO}$, $=\text{SO}_2$, $=\text{NR}_1$, $=\text{PR}_1$, $=\text{P}(\text{O})\text{R}_1$, in which M_1 is Si, Ge, or Sn; R_1 and R_2 , equal or different, are alkyl groups with 1-4 carbon atoms or aryl groups with 6-10 carbon atoms; a , b , c are, independently, integers from 0 to 4; e is an integer from 1 to 6 and two or more of the radicals R^1 , R^2 and R^3 can form a ring. In the case when the Cp group is substituted, the substituent is preferably an alkyl group with 1-20 carbon atoms.

Representative compounds having formula (I) comprise:

$(\text{Me}_5\text{Cp})\text{MMe}_3$, $(\text{Me}_5\text{Cp})\text{M}(\text{OMe})_3$, $(\text{Me}_5\text{Cp})\text{MCl}_3$, $(\text{Cp})\text{MCl}_3$, $(\text{Cp})\text{MMe}_3$, $(\text{MeCp})\text{MMe}_3$, $(\text{Me}_3\text{Cp})\text{MMe}_3$, $(\text{Me}_4\text{Cp})\text{MCl}_3$, $(\text{Ind})\text{MBenz}_3$, $(\text{H}_4\text{Ind})\text{MBenz}_3$, $(\text{Cp})\text{MBu}_3$.

Representative compounds having formula (II) comprise:

$(\text{Cp})_2\text{MMe}_2$, $(\text{Cp})_2\text{MPh}_2$, $(\text{Cp})_2\text{MET}_2$, $(\text{Cp})_2\text{MCl}_2$, $(\text{Cp})_2\text{M}(\text{OMe})_2$, $(\text{Cp})_2\text{M}(\text{OMe})\text{Cl}$, $(\text{MeCp})_2\text{MCl}_2$, $(\text{Me}_5\text{Cp})_2\text{MCl}_2$, $(\text{Me}_5\text{Cp})_2\text{MMe}_2$, $(\text{Me}_5\text{Cp})_2\text{MMeCl}$, $(\text{Cp})(\text{Me}_5\text{Cp})\text{MCl}_2$, $(1\text{-MeFlu})_2\text{MCl}_2$, $(\text{BuCp})_2\text{MCl}_2$, $(\text{Me}_3\text{Cp})_2\text{MCl}_2$, $(\text{Me}_4\text{Cp})_2\text{MCl}_2$, $(\text{Me}_5\text{Cp})_2\text{M}(\text{OMe})_2$, $(\text{Me}_5\text{Cp})_2\text{M}(\text{OH})\text{Cl}$,

$(\text{Me}_5\text{Cp})_2\text{M}(\text{OH})_2$, $(\text{Me}_5\text{Cp})_2\text{M}(\text{C}_6\text{H}_5)_2$, $(\text{Me}_5\text{Cp})_2\text{M}(\text{CH}_3)\text{Cl}$,
 $(\text{EtMe}_4\text{Cp})_2\text{MCl}_2$, $[(\text{C}_6\text{H}_5)\text{Me}_4\text{Cp}]_2\text{MCl}_2$, $(\text{Et}_5\text{Cp})_2\text{MCl}_2$,
 $(\text{Me}_5\text{Cp})_2\text{M}(\text{C}_6\text{H}_5)\text{Cl}$, $(\text{Ind})_2\text{MCl}_2$, $(\text{Ind})_2\text{MMe}_2$, $(\text{H}_4\text{Ind})_2\text{MCl}_2$,
 $(\text{H}_4\text{Ind})_2\text{MMe}_2$, $\{[\text{Si}(\text{CH}_3)_3]\text{Cp}\}_2\text{MCl}_2$, $\{[\text{Si}(\text{CH}_3)_3]_2\text{Cp}\}_2\text{MCl}_2$,
 $(\text{Me}_4\text{Cp})(\text{Me}_5\text{Cp})\text{MCl}_2$.

Representative compounds of formula (III) comprise:

$\text{C}_2\text{H}_4(\text{Ind})_2\text{MCl}_2$, $\text{C}_2\text{H}_4(\text{Ind})_2\text{MMe}_2$, $\text{C}_2\text{H}_4(\text{H}_4\text{Ind})_2\text{MCl}_2$, $\text{C}_2\text{H}_4(\text{H}_4\text{Ind})_2\text{MMe}_2$,
 $\text{Me}_2\text{Si}(\text{Me}_4\text{Cp})_2\text{MCl}_2$, $\text{Me}_2\text{Si}(\text{Me}_4\text{Cp})_2\text{MMe}_2$, $\text{Me}_2\text{SiCp}_2\text{MCl}_2$, $\text{Me}_2\text{SiCp}_2\text{MMe}_2$,
 $\text{Me}_2\text{Si}(\text{Me}_4\text{Cp})_2\text{MMeOMe}$, $\text{Me}_2\text{Si}(\text{Flu})_2\text{MCl}_2$, $\text{Me}_2\text{Si}(2\text{-Et-5-iPrCp})_2\text{MCl}_2$,
 $\text{Me}_2\text{Si}(\text{H}_4\text{Ind})_2\text{MCl}_2$, $\text{Me}_2\text{Si}(\text{H}_4\text{Flu})_2\text{MCl}_2$, $\text{Me}_2\text{SiCH}_2(\text{Ind})_2\text{MCl}_2$, $\text{Me}_2\text{Si}(2\text{-Me- H}_4\text{Ind})_2\text{MCl}_2$,
 $\text{Me}_2\text{Si}(2\text{-MeInd})_2\text{MCl}_2$, $\text{Me}_2\text{Si}(2\text{-Et-5-iPr-Cp})_2\text{MCl}_2$,
 $\text{Me}_2\text{Si}(2\text{-Me-5-EtCp})_2\text{MCl}_2$, $\text{Me}_2\text{Si}(2\text{-Me-5-Me-Cp})_2\text{MCl}_2$, $\text{Me}_2\text{Si}(2\text{-Me-4,5-benzoindenyl})_2\text{MCl}_2$,
 $\text{Me}_2\text{Si}(4,5\text{-benzoindenyl})_2\text{MCl}_2$, $\text{Me}_2\text{Si}(2\text{-EtInd})_2\text{MCl}_2$, $\text{Me}_2\text{Si}(2\text{-iPr-Ind})_2\text{MCl}_2$, $\text{Me}_2\text{Si}(2\text{-t-butyl-Ind})\text{MCl}_2$,
 $\text{Me}_2\text{Si}(3\text{-t-butyl-5-MeCp})_2\text{MCl}_2$, $\text{Me}_2\text{Si}(3\text{-t-butyl-5-MeCp})_2\text{MMe}_2$,
 $\text{Me}_2\text{Si}(2\text{-MeInd})_2\text{MCl}_2$, $\text{C}_2\text{H}_4(2\text{-Me-4,5-benzoindenyl})_2\text{MCl}_2$,
 $\text{Me}_2\text{C}(\text{Flu})\text{CpMCl}_2$, $\text{Ph}_2\text{Si}(\text{Ind})_2\text{MCl}_2$, $\text{Ph}(\text{Me})\text{Si}(\text{Ind})_2\text{MCl}_2$,
 $\text{C}_2\text{H}_4(\text{H}_4\text{Ind})\text{M}(\text{NMe}_2)\text{OMe}$, isopropylidene-(3-t-butyl-Cp)(Flu)MCl₂,
 $\text{Me}_2\text{C}(\text{Me}_4\text{Cp})(\text{MeCp})\text{MCl}_2$, $\text{MeSi}(\text{Ind})_2\text{MCl}_2$, $\text{Me}_2\text{Si}(\text{Ind})_2\text{MMe}_2$,
 $\text{Me}_2\text{Si}(\text{Me}_4\text{Cp})_2\text{MCl}(\text{OEt})$, $\text{C}_2\text{H}_4(\text{Ind})_2\text{M}(\text{NMe}_2)_2$, $\text{C}_2\text{H}_4(\text{Me}_4\text{Cp})_2\text{MCl}_2$,
 $\text{C}_2\text{Me}_4(\text{Ind})_2\text{MCl}_2$, $\text{Me}_2\text{Si}(3\text{-Me-Ind})_2\text{MCl}_2$, $\text{C}_2\text{H}_4(2\text{-Me-Ind})_2\text{MCl}_2$,
 $\text{C}_2\text{H}_4(3\text{-Me-Ind})_2\text{MCl}_2$, $\text{C}_2\text{H}_4(4,7\text{-Me}_2\text{-Ind})_2\text{MCl}_2$, $\text{C}_2\text{H}_4(5,6\text{-Me}_2\text{-Ind})_2\text{MCl}_2$,
 $\text{C}_2\text{H}_4(2,4,7\text{-Me}_3\text{Ind})_2\text{MCl}_2$, $\text{C}_2\text{H}_4(3,4,7\text{-Me}_3\text{Ind})_2\text{MCl}_2$,
 $\text{C}_2\text{H}_4(2\text{-Me-H}_4\text{Ind})_2\text{MCl}_2$, $\text{C}_2\text{H}_4(4,7\text{-Me}_2\text{-H}_4\text{Ind})_2\text{MCl}_2$, $\text{C}_2\text{H}_4(2,4,7\text{-Me}_3\text{-H}_4\text{Ind})_2\text{MCl}_2$,
 $\text{Me}_2\text{Si}(4,7\text{-Me}_2\text{-Ind})_2\text{MCl}_2$, $\text{Me}_2\text{Si}(5,6\text{-Me}_2\text{-Ind})_2\text{MCl}_2$,
 $\text{Me}_2\text{Si}(2,4,7\text{-Me}_3\text{-H}_4\text{Ind})_2\text{MCl}_2$.

In the simplified formulae given above the symbols have the following meanings: Me=methyl, Et=ethyl, iPr=isopropyl, Bu=butyl, Ph=phenyl, Cp=cyclopentadienyl, Ind=indenyl,

H₄Ind=4,5,6,7-tetrahydroindenyl, Flu=fluorenyl, Benz=benzyl, M=Ti, Zr or Hf, preferably Zr.

Compounds of the type Me₂Si(2-Me-Ind)₂ZrCl₂ and Me₂Si(2-Me-H₄Ind)ZrCl₂ and their methods of preparation are described respectively in European Applications EP-A-485822 and 485820, the description of which is included herein for reference.

Compounds of the type Me₂Si(3-t-butyl-5-MeCp)₂ZrCl₂ and of the type Me₂Si(2-Me-4,5-benzoindenyl)ZrCl₂ and their method of preparation are described respectively in Patent USP 5132262 and in Patent Application EP-A-549900, the description of which is included herein for reference.

The first stage of polymerization (A) can be carried out in liquid phase or in gas phase, working in one or more reactors. The liquid phase can consist of an inert hydrocarbon solvent (suspension process) or of one or more olefins CH₂=CHR (liquid monomer process). Gas-phase polymerization can be carried out using the known fluidized-bed technique or working in conditions in which the bed is mechanically stirred.

The treatment stage (B) is carried out advantageously in two parts, (a) first bringing into contact the polymer produced in polymerization stage (A) with compounds that are able to deactivate the catalyst used in said stage (A), and then (b), bringing into contact the product obtained in (a) with solutions of the transition metal M in hydrocarbon solvents (benzene, toluene, heptane, hexane, liquid propane and the like).

Examples of compounds that can be used in treatment stage (a) can be selected from the group consisting of compounds having the general formula R_{y-1}XH in which R is hydrogen or a hydrocarbon group with from 1 to 10 carbon atoms, X is O, N, or S, and y is the valency of X.

Non-limitative examples of such compounds are represented by alcohols, thioalcohols, mono- and di-alkylamines, NH_3 , H_2O and H_2S . Preferred compounds are those in which X is O and among these, a particularly preferred compound is water.

Other examples of compounds that can be used in treatment stage (a) are CO, COS, CS_2 , CO_2 , O_2 and acetylenic or allenic compounds.

The molar ratio between the deactivating compound and the compound of the transition metal M^{I} should preferably be such as to ensure substantial deactivation of the catalyst of stage (A). The value of this ratio is preferably greater than 50, more preferably greater than 150 and in particular greater than 250.

Treatment (a), in which these deactivating compounds are brought into contact with the polymer produced in stage (A), can be effected in various ways. In one of these, the polymer is brought into contact, for a time ranging from 1 minute to some hours, with a hydrocarbon solvent that contains the deactivating compound in solution, suspension or dispersion. An example of dispersion of the deactivating compound in a hydrocarbon solvent is represented by humidified hexane. At the end of treatment (a) the liquid is removed and the polymer undergoes treatment (b).

Treatment (b) is preferably carried out using the compound of the transition metal M in solutions of hydrocarbon solvents containing a dissolved alkyl-Al compound, such as triisobutyl-Al, triethyl-Al and/or an aluminoxane, for example polymethylaluminoxane (MAO), tetraisobutylaluminoxane or tetra(2,5-dimethylhexyl)-aluminoxane. The molar ratio of the alkyl-Al compound to the compound of the transition metal M is greater than 2 and is preferably between 5 and 1000. The said treatment (b) can be carried out by suspending the polymer obtained from stage

(a) in hydrocarbon solvents containing the dissolved compound of transition metal M, and optionally an alkyl-Al compound and/or an aluminoxane, generally working at temperature between 0 and 100°C, preferably between 10 and 60°C, and removing the solvent at the end of the treatment. Alternatively, the polymer obtained from (a) can be brought into contact, dry, with solutions of the compound of the transition metal M containing the minimum quantity of solvent for keeping the said compound in solution. Stage (B) can be conveniently carried out in the gas phase in a loop reactor, in which the polymer produced in the first stage of polymerization is circulated by a stream of inert gas. Solutions of the deactivating compound and of the compound of the transition metal M are fed successively, for example using a sprayer, to the loop reactor in the gas phase, and a free-flowing product is obtained at the end of the treatment. Conveniently, before stage (b), the product is treated with compounds that are able to decontaminate the system, for example with alkyl-Al compounds.

The quantity of compound of the transition metal M, expressed as metal, contained in the product obtained from stage (B), can vary over a wide range depending on the compound of transition metal M used and on the relative quantity of product that it is desired to produce in the various stages. Generally this quantity is between $1 \cdot 10^{-7}$ and $5 \cdot 10^{-3}$ g of metal M/g of product, preferably between $5 \cdot 10^{-7}$ and $5 \cdot 10^{-4}$, more preferably between $1 \cdot 10^{-6}$ and $1 \cdot 10^{-4}$.

The second stage of polymerization (C) can be carried out in liquid phase or in gas phase, working in one or more reactors. The liquid phase can consist of an inert hydrocarbon solvent (suspension process) or of one or more olefins $\text{CH}_2=\text{CHR}$ (li-

quid monomer process). Gas-phase polymerization can be carried out in reactors with a fluidized bed or with a mechanically-stirred bed. During said stage (C), it is convenient to feed, to the polymerization reactor, an alkyl-Al compound selected from Al-trialkyls in which the alkyl groups have 1-12 carbon atoms, and linear or cyclic aluminoxane compounds containing the repeat unit $-(R_4)AlO-$ in which R_4 is an alkyl group with 1-12 carbon atoms or a cycloalkyl or aryl group with 6-10 carbon atoms, the said aluminoxane compounds containing from 1 to 50 repeat units. As a rule the alkyl-Al compound is fed to polymerization stage (C) when treatment (b) in stage (B) is carried out in the absence of alkyl-Al compounds.

The advantages of the process according to the present invention are found both in the quality of the final product and in the flexibility of the process. Treatment stage (B) in fact makes it possible to work with different catalytic systems in polymerization stages (A) and (C).

In particular, in the absence of treatment (a), it would be necessary to produce too high amounts of polymer in stage (A) so as to exhaust the activity of the catalyst itself in this stage. However, this would involve production of too large quantities of product that comes from the said stage. This would result either in the production of a final product in which the portion that derives from stage (A) of the process would largely predominate, or alternatively production of a final product with fractions that come from stages (A) and (C) that are balanced, but with unsuitable dimensions of the polymer particles.

The process of the invention can be used for preparing a wide range of olefin polymer compositions. In particular, the process of the invention is particularly suitable for the pro-

duction of high-impact polypropylene (heterophase copolymers of propylene). In such a case it is possible to obtain elastomeric copolymers in which there are no relatively long sequences of the same monomer unit and, therefore, to obtain copolymers with valuable elastomeric properties.

In fact, a further aspect of the present invention is a process for the preparation of heterophase copolymers of propylene, characterized in that it comprises:

- (A) a first stage of polymerization in which, in one or more reactors, propylene and possibly ethylene and/or one or more olefins $\text{CH}_2=\text{CHR}^{\text{II}}$, where R^{II} is a hydrocarbon radical with 2-10 carbon atoms, are polymerized in the presence of a catalyst comprising the product of the reaction between an alkyl-Al compound, optionally an electron-donor compound (external donor) and a solid component comprising at least one compound of a transition metal M^{I} selected from titanium and vanadium and not containing $\text{M}^{\text{I}}-\pi$ bonds, a magnesium halide in active form and optionally an electron-donor compound (internal donor), obtaining an olefin polymer that has porosity, expressed as percentage of voids, greater than 10%, content of units derived from ethylene and/or from the $\text{CH}_2=\text{CHR}^{\text{II}}$ olefin less than 20% by weight, content of units derived from propylene greater than 80% by weight and insolubility in xylene greater than 60%;
 - (B) a treatment stage in which the product obtained in said stage (A) is, in any order whatever:
 - (a) brought into contact with a compound that is capable of deactivating the catalyst present in stage (A);
- and,

- (b) brought into contact with a compound of a transition metal M selected from Ti, V, Zr and Hf containing at least one M- π bond and optionally with an alkyl-Al compound;
- (C) a second stage of polymerization in which, in one or more reactors, one or more olefins $\text{CH}_2=\text{CHR}$, where R is hydrogen or an alkyl, cycloalkyl or aryl radical with 1-10 carbon atoms, are polymerized in the presence of the product obtained in stage (B), obtaining a substantially amorphous olefin (co)polymer in quantity between 20 and 80% by weight based on the total amount of polymer produced in stages (A) and (C).

The polymer produced in said first stage of polymerization (A) is preferably a homopolymer of propylene with high isotacticity index, or a crystalline copolymer of propylene that has a content by weight of units derived from ethylene and/or from the $\text{CH}_2=\text{CHR}^{\text{II}}$ olefin below 10%.

Non-limitative examples of substantially amorphous olefin (co)polymers that can be prepared in stage (C) are the elastomeric copolymers of ethylene and propylene and the elastomeric terpolymers of ethylene and propylene with smaller proportions of a diene, which have a content by weight of units derived from ethylene between about 30 and 70%; the elastomeric copolymers of ethylene and butene and the elastomeric terpolymers of ethylene, butene and propylene having a content by weight of units derived from ethylene between about 30 and 70%; the atactic polypropylenes with high molecular weight ($\eta > 1$). Examples of these copolymers are described in European Patent Applications EP-A-586658, EP-A-604917 and in Italian Patent Applications MI-93A000943, MI-93A001405, MI-93A001406, MI-

93A001960 and MI-93A001963, to which reference is made for the part relating to the characteristics of the products and to the catalysts used in their production.

Polymerization stage (A) can be conveniently carried out in liquid propylene, working in one or more loop reactors, or in the gas phase, working in one or more reactors with fluidized bed or mechanically stirred bed. The gas-phase technology with a fluidized-bed is preferred.

Polymerization stage (C) is preferably carried out in one or more reactor in the gas-phase, with a fluidized-bed. Other technologies (for example suspension polymerization or gas-phase polymerization with mechanically stirred bed) can be used.

The porosity (expressed as percentage of voids) of the polymer produced in the first stage of polymerization (A) is preferably greater than 15% and more preferably greater than 20%. The distribution of pore radius is such that more than 40% of the porosity is due to pores with diameter greater than 10000 Å. Preferably, and for high values of porosity, more than 90% of the porosity is due to pores with diameter greater than 10000 Å.

The amount of polymer produced in polymerization stage (C) is preferably between 25% and 75%, more preferably between 35% and 65% by weight based on the total amount of polymer produced in stages (A) and (C).

The process is preferably carried out continuously, working in both stages of polymerization (A) and (C) in gas-phase fluidized-bed reactors and effecting stage (B) in a gas-phase loop reactor. Polymerization stage (A) is preferably preceded by a stage of prepolymerization in which propylene or its mixtures with ethylene and/or $\text{CH}_2=\text{CHR}^{\text{II}}$ olefins are polymerized in the

presence of the catalyst described in (A) in a quantity of between 5 and 500 g/g catalyst.

The following examples are given to better illustrate the invention but do not limit it.

The properties indicated are determined with the following methods:

- Porosity and surface with nitrogen: are determined according to B.E.T. methodology (equipment used: SORPTOMATIC 1800 from Carlo Erba).
- Size of catalyst particles: is determined by a method based on the principle of optical diffraction of monochromatic laser light with the "Malvern Instr. 2600" apparatus. The mean size is stated as P50.
- Melt Index E (MIE): determined according to ASTM-D 1238, method E.
- Melt Index F (MIF): determined according to ASTM-D 1238, method F.
- Ratio of degrees (F/E): ratio of Melt Index F to Melt Index E.
- Melt Index L (MIL): determined according to ASTM-D 1238, method L.
- Flowability: is the time taken for 100 g of polymer to flow through a funnel whose discharge hole has a diameter of 1.25 cm and whose walls are inclined at 20° to the vertical.
- Density: DIN 53194.
- Morphology and particle size distribution of the polymer particles: ASTM-D 1921-63.

- Fraction soluble in xylene: measured by dissolving the polymer in boiling xylene and determining the insoluble residue after cooling to 25°C.
- Content of comonomer: percentage by weight of comonomer determined by IR spectroscopy.
- Effective density: ASTM-D 792.
- Porosity: the porosity expressed as percentage of voids is determined by absorption of mercury under pressure. The volume of mercury absorbed corresponds to the volume of the pores. For this determination, a calibrated dilatometer (diameter 3 mm) CD3 (Carlo Erba) connected to a reservoir of mercury and to a high-vacuum pump ($1 \cdot 10^{-2}$ mba) is used. A weighed amount of sample (about 0.5 g) is placed in the dilatometer. The apparatus is then placed under high vacuum (<0.1 mm Hg) and is kept in these conditions for 10 minutes. The dilatometer is then connected to the mercury reservoir and the mercury is allowed to flow slowly into it until it reaches the level marked on the dilatometer at a height of 10 cm. The valve that connects the dilatometer to the vacuum pump is closed and the apparatus is pressurized with nitrogen (2.5 kg/cm^2). Under the effect of the pressure, the mercury penetrates into the pores and the level goes down according to the porosity of the material. Once the level at which the mercury has stabilized has been measured on the dilatometer, the volume of the pores is calculated from the equation $V = R^2 \cdot \pi \cdot \Delta H$, where R is the radius of the dilatometer and ΔH is the difference in cm between the initial and final level of the mercury in the dilatometer. By weighing the dilatometer, dilatometer+mercury, dilatometer+mercury+sample, the value of the apparent volume V_1 of

the sample prior to penetration of the pores can be calculated. The volume of the sample is given by:

$$V_1 = [P_1 - (P_2 - P)] / D$$

where P is the weight of the sample in grams, P_1 is the weight of the dilatometer+mercury in grams, P_2 is the weight of the dilatometer+mercury+sample in grams, D is the density of mercury (at 25°C = 13.546 g/cm³). The percentage porosity is given by the relation $X = (100 \cdot V) / V_1$.

- Intrinsic viscosity (IV): determined in tetrahydronaphthalene at 135°C.

EXAMPLES

EXAMPLE 1 (comparative)

Stage (A): Preparation of PP homopolymer

In a 50 ml glass flask, 0.0161 g of a solid catalytic component, prepared according to Example 3 of European Patent Application EP-A-395083, was pre-contacted with 0.799 g of triethylaluminium (TEAL) and 0.31 g of cyclohexylmethyldimethoxysilane (CMMS) in 8 ml of anhydrous hexane. The mixture was introduced into a 4.25-litre steel autoclave which was previously purged with successive washings first with hexane at 80°C for one hour and then with gaseous propylene at 80°C for one hour. Next, 1752 g of liquid propylene were introduced together with 982 ml of hydrogen at 30°C. The temperature was raised to 70°C and polymerization was carried out for 180 minutes, obtaining 248 g of polypropylene with the following characteristics: IV=1.55dl/g; xylene-insoluble matter =96% by weight.

Stage (C): Copolymerization of ethylene and propylene

After removing the propylene, the same reactor was charged with 500 g of liquid propane at a temperature of 50°C and a

pressure of 19.5 bar. Then 7 mmol of M-MAO, dissolved in ISOPAR C, were introduced, and the mixture was left in contact with the polymer for 10 minutes at 50°C. The propane was removed by evaporation at 50°C and some washings with gaseous propylene were effected at 50°C to eliminate the residual propane. 19.3 g of ethylene and 41.6 g of propylene were added to the polymer thus obtained, in the same reactor at 50°C. Polymerization was carried out by introducing a mixture of the two monomers containing 60% by weight of ethylene. Copolymerization was carried out at 50°C and at 9 bar for 120 minutes. 276 g of copolymer, having the characteristics shown in Table 1, were obtained.

EXAMPLE 2 (comparative)

Stage (A): Preparation of PP homopolymer

The catalyst and the propylene homopolymer were prepared as described in Stage A of Example 1. Polymerization was carried out using 0.0132 g of solid catalytic component. 209 g of homopolymer with the following characteristics were obtained: IV=1.57 dl/g; insoluble in xylene =96.1% by weight.

Stage (B): Treatment (b) with EBTHI-ZrCl₂

After eliminating the propylene 1, the same reactor was charged with 500 g of liquid propane at a temperature of 50°C and a pressure of 19.5 bar. Then 0.005 g of EBTHI-ZrCl₂ precontacted in ISOPAR C with 11.7 mmol of M-MAO at 25°C for 10 minutes were introduced. The mixture was left in contact with the polymer for 10 minutes at 50°C. The propane was removed by evaporation at 50°C and some washings were effected with gaseous propylene at 50°C to eliminate the residual propane.

Stage (C): Copolymerization of ethylene and propylene

The procedure described in Stage (C) of Example 1 was followed, carrying out copolymerization for 240 minutes and

obtaining 381 g of copolymer with the characteristics shown in Table 1.

EXAMPLE 3

Stage (A): Preparation of PP homopolymer

The catalyst and the propylene homopolymer were prepared as described in Stage (A) of Example 1. Polymerization was carried out using 0.0146 g of solid catalytic component, obtaining 186 g of homopolymer that has the following characteristics: IV=1.55 dl/g; insoluble in xylene =95.9% by weight.

Stage (B): Treatment (a) with H₂O and treatment (b) with EBTHI-ZrCl₂

After degassing the propylene, the same reactor was charged with 1000 ml of hexane humidified with 0.0513 g of H₂O. It was left in contact with the polymer at 50°C for 30 minutes, in a nitrogen atmosphere. The liquid was eliminated by siphoning and some washings were carried out at room temperature with cycles of vacuum/nitrogen. The same reactor was charged with 500 g of liquid propane at a temperature of 50°C and pressure of 19.5 bar. Then 0.005 g of EBTHI-ZrCl₂, precontacted in ISOPAR C with 11.7 mmol of M-MAO at 25°C for 10 minutes, were introduced. The polymer was left in contact with this mixture for 10 minutes at 50°C. The propane was removed by evaporation at 50°C and some washings were effected with gaseous propylene at 50°C to eliminate the residual propane.

Stage (C): Copolymerization of ethylene and propylene

The procedure described in Stage (C) of Example 1 was followed, copolymerizing for 50 minutes and obtaining 256 g of copolymer having the characteristics shown in Table 1.

EXAMPLE 4 (comparative)

Stage (A): Preparation of PP homopolymer

In a 50 ml glass flask, 0.0187 g of a solid catalytic component, prepared according to Example 3 of European Patent Application EP-A-395083, were pre-contacted with 1.48 g of triisobutylaluminium (TIBAL) and 0.0706 g of cyclohexylmethyldimethoxysilane (CMMS) in 8 ml of anhydrous hexane. The mixture was placed in a 4.25-litre steel autoclave which was previously purged with successive washings first with hexane at 80°C for one hour and then with gaseous propylene at 80°C for one hour. Then 1286 g of liquid propylene were introduced at 30°C. The temperature was raised to 70°C and polymerization was carried out for 120 minutes, obtaining 32 g of homopolymer having the following characteristics: IV=5.68 dl/g; insoluble in xylene =89.7% by weight.

Stage (C): Copolymerization of ethylene and propylene

After degassing the propylene, the same reactor was charged with 500 g of liquid propane at a temperature of 50°C and pressure of 19.5 bar. Then 9.38 mmol of TIBAO, dissolved in cyclohexane, were introduced, and the mixture was left in contact with the polymer for 10 minutes at 50°C. The propane was removed by evaporation at 50°C and some washings were effected with gaseous propylene at 50°C to eliminate the residual propane. 33.8 g of ethylene and 72.9 g of propylene were added to the product thus obtained, in the same reactor at 50°C. The composition of the copolymer was kept constant by feeding a mixture of the two monomers containing 60% by weight of ethylene. Copolymerization was carried out at 50°C and at 15 bar for 245 minutes. 315 g of copolymer with the characteristics shown in Table 2 were obtained.

EXAMPLE 5 (comparative)

Stage (A): Preparation of PP homopolymer

The catalyst and the propylene homopolymer were prepared as described in Stage (A) of Example 4. Polymerization was carried out using 0.02 g of solid catalytic component, obtaining 69 g of homopolymer having the following characteristics: IV=4.69 dl/g; insoluble in xylene =82% by weight.

Stage (B): treatment (b) with EBTHI-ZrCl₂

After degassing the propylene, the same reactor was charged with 500 g of liquid propane at a temperature of 50°C and pressure of 19.5 bar. Then 0.004 g of EBTHI-ZrCl₂, pre-contacted in cyclohexane with 9.38 mmol of TIBAO at 25°C for 10 minutes, were introduced. The mixture was left in contact with the polymer for 10 minutes at 50°C. The propane was removed by evaporation at 50°C and some washings were effected with gaseous propylene at 50°C to eliminate the residual propane.

Stage (C): Copolymerization of ethylene and propylene

The procedure described in Stage (C) of Example 1 was followed, copolymerizing for 54 minutes and obtaining 353 g of copolymer having the characteristics shown in Table 2.

EXAMPLE 6

Stage (A): Preparation of PP homopolymer

The catalyst and the propylene homopolymer were prepared as described in Stage (A) of Example 4. Polymerization was carried out using 0.0414 g of solid catalytic component, obtaining 170 g of homopolymer having the following characteristics: IV=4.4 dl/g; insoluble in xylene =85.3% by weight.

Stage (B): Treatment (a) with H₂O and treatment (b) with EBTHI-ZrCl₂

After degassing the propylene, the same reactor was charged with 1000 ml of hexane humidified with 0.068 g of H₂O. It was left in contact with the polymer at 50°C for 30 minutes, in a

nitrogen atmosphere. The liquid was removed by siphoning and some washings were carried out at room temperature with cycles of vacuum/nitrogen. Then the same reactor was loaded with 1.48 g of TIBAL dissolved in 500 g of liquid propane at a temperature of 50°C and pressure of 19.5 bar. The polymer was left in contact with this mixture for 20 minutes at 50°C. Then 0.020 g of EBTHI-ZrCl₂, pre-contacted in cyclohexane with 46.9 mmol of Ti-BAO at 25°C for 10 minutes, were introduced. The polymer was left in contact with this mixture for 10 minutes at 50°C. The propane was removed by evaporation at 50°C and some washings were carried out with gaseous propylene at 50°C to eliminate the residual propane.

Stage (C): Copolymerization of ethylene and propylene

The procedure described in Stage (C) of Example 1 was followed, carrying out the copolymerization for 81 minutes and obtaining 260 g of copolymer having the characteristics shown in Table 2.

TABLE 1

Characteristics of the copolymers of Examples 1-3

Example		1	2	3
EPR	% by weight	21.4	53.8	40.2
M.p. DSC *	°C	118	116	--
M.p. DSC *	°C	167	164	166
Xylene-sol.	% by weight	12.9	43.9	42
Xylene-insol.	% by weight	87.1	56.1	58
IV homopolym.	dl/g	1.55	1.57	1.55
IV final	dl/g	2.77	2.71	1.24

TABLE 2
Characteristics of the copolymers of Examples 4-6




Example	No.	4	5	6
EPR	% by weight	90	82	35
M.p. DSC *	°C	116	113	--
M.p. DSC *	°C	158	156	159
Xylene-sol.	% by weight	53.2	58.4	41.1
Xylene-insol.	% by weight	44.7	39.8	57.9
IV homopolym.	dl/g	5.68	4.69	4.4
IV final	dl/g	8.81	6.35	2.96

* The region of the thermogram between 100-180°C is examined, in which the melting-point peaks of PP homopolymer and of the semi-crystalline fraction of the rubber, if produced, can appear.

CLAIMS


1. Multistage process for the polymerization of one or more olefins with the formula $\text{CH}_2=\text{CHR}$, in which R is hydrogen or an alkyl, cycloalkyl or aryl group having from 1 to 10 carbon atoms, characterized in that it comprises:
 - (A) a first stage of polymerization in which one or more of the said olefins are polymerized, in one or more reactors, in the presence of a catalyst comprising the product of reaction between an alkyl-Al compound and a solid component comprising a compound of a transition metal M^{I} selected from Ti and V, not containing M- π bonds, a halide of Mg in active form, to produce an olefin homo or copolymer;
 - (B) a treatment stage in which the product obtained in the first stage of polymerization (A) is, in any order whatever:
 - (a) brought into contact with a compound capable of deactivating the catalyst present in the stage (A); and,
 - (b) brought into contact with a compound of a transition metal M selected from Ti, Zr, V, or Hf containing at least one M- π bond and optionally with an alkyl-Al compound;
 - (C) a second stage of polymerization in which one or more of the said olefins are polymerized, in one or more reactors, in the presence of the product obtained in treatment stage (B).
2. Process according to Claim 1 in which the olefin homo or copolymer produced in stage (A) has a porosity, expressed as percentage of voids, greater than 5%.

3. Process according to Claim 2 in which the olefin homo or copolymer produced in stage (A) has a porosity, expressed as percentage of voids, greater than 10%.
4. Process according to Claim 1, in which the magnesium halide in active form is MgCl_2 and the compound of the transition metal M^{I} is selected from the group consisting of: halides of Ti, halo-alcoholates of Ti, VCl_3 , VCl_4 , VOCl_3 and halo-alcoholates of V.
5. Process according to Claim 4, in which the compound of Ti is selected from the group consisting of: TiCl_4 , TiCl_3 and halo-alcoholates of formula $\text{Ti}(\text{OR}^{\text{I}})_m\text{X}_n$, in which R^{I} is a hydrocarbon radical with 1-12 carbon atoms or a $-\text{COR}^{\text{I}}$ group, X is a halogen and $(m+n)$ is the valency of the Ti.
6. Process according to Claim 1, in which the solid component used in the first stage of polymerization (A) is in the form of spheroidal particles with a mean diameter of between 10 and 150 μm .
7. Process according to Claim 1, in which the compound of the transition metal M comprises at least one ligand L coordinated on the metal, the said ligand L having a mono- or polycyclic structure containing conjugated π electrons.
8. Process according to Claim 7, in which the compound of the transition metal M is selected from:




in which M is Ti, V, Zr or Hf; Cp^{I} and Cp^{II} , equal or different, are cyclopentadienyl groups or substituted cyclopentadienyl groups; two or more substituents on the said cyclopentadienyl groups can form one or more rings

having from 4 to 6 carbon atoms; R^1 , R^2 and R^3 , equal or different, are atoms of hydrogen, halogen, an alkyl or alkoxy group with 1-20 carbon atoms, aryl, alkylaryl or arylalkyl with 6-20 carbon atoms, an acyloxy group with 1-20 carbon atoms, an allyl group, a substituent containing a silicon atom; A is an alkenyl bridge or one with structure selected from:




$=AlR_1$, $-Ge-$, $-Sn-$, $-O-$, $-S-$, $=SO$, $=SO_2$, $=NR_1$, $=PR_1$, $=P(O)R_1$, in which M_1 is Si, Ge, or Sn; R_1 and R_2 , equal or different, are alkyl groups with 1-4 carbon atoms or aryl groups with 6-10 carbon atoms; a , b , c are, independently, integers from 0 to 4; e is an integer from 0 to 6 and two or more of the radicals R^1 , R^2 and R^3 can form a ring.

9. Process according to Claim 7, in which the compound of the transition metal is selected from the compounds having structure:



10. Process according to Claim 7, in which the compound of the transition metal is selected from the compounds having the structure:



$(EtMe_4Cp)_2MCl_2$, $[(C_6H_5)Me_4Cp]_2MCl_2$, $(Et_5Cp)_2MCl_2$, $(Me_5Cp)_2M(C_6H_5)Cl$, $(Ind)_2MCl_2$, $(Ind)_2MMe_2$, $(H_4Ind)_2MCl_2$, $(H_4Ind)_2MMe_2$, $\{[Si(CH_3)_3]Cp\}_2MCl_2$, $\{[Si(CH_3)_3]_2Cp\}_2MCl_2$, $(Me_4Cp)(Me_5Cp)MCl_2$.

11. Process according to Claim 7, in which the compound of the transition metal is selected from the compounds having the structure:

$C_2H_4(Ind)_2MCl_2$, $C_2H_4(Ind)_2MMe_2$, $C_2H_4(H_4Ind)_2MCl_2$, $C_2H_4(H_4Ind)_2MMe_2$, $Me_2Si(Me_4Cp)_2MCl_2$, $Me_2Si(Me_4Cp)_2MMe_2$, $Me_2SiCp_2MCl_2$, $Me_2SiCp_2MMe_2$, $Me_2Si(Me_4Cp)_2MMeOMe$, $Me_2Si(Flu)_2MCl_2$, $Me_2Si(2-Et-5-iPrCp)_2MCl_2$, $Me_2Si(H_4Ind)_2MCl_2$, $Me_2Si(H_4Flu)_2MCl_2$, $Me_2SiCH_2(Ind)_2MCl_2$, $Me_2Si(2-Me-H_4Ind)_2MCl_2$, $Me_2Si(2-MeInd)_2MCl_2$, $Me_2Si(2-Et-5-iPr-Cp)_2MCl_2$, $Me_2Si(2-Me-5-EtCp)_2MCl_2$, $Me_2Si(2-Me-5-Me-Cp)_2MCl_2$, $Me_2Si(2-Me-4,5-benzoindenyl)_2MCl_2$, $Me_2Si(4,5-benzoindenyl)_2MCl_2$, $Me_2Si(2-EtInd)_2MCl_2$, $Me_2Si(2-iPr-Ind)_2MCl_2$, $Me_2Si(2-t-butyl-Ind)MCl_2$, $Me_2Si(3-t-butyl-5-MeCp)_2MCl_2$, $Me_2Si(3-t-butyl-5-MeCp)_2MMe_2$, $Me_2Si(2-MeInd)_2MCl_2$, $C_2H_4(2-Me-4,5-benzoindenyl)_2MCl_2$, $Me_2C(Flu)CpMCl_2$, $Ph_2Si(Ind)_2MCl_2$, $Ph(Me)Si(Ind)_2MCl_2$, $C_2H_4(H_4Ind)M(NMe_2)OMe$, isopropylidene-(3-t-butyl-Cp)(Flu)MCl₂, $Me_2C(Me_4Cp)(MeCp)MCl_2$, $MeSi(Ind)_2MCl_2$, $Me_2Si(Ind)_2MMe_2$, $Me_2Si(Me_4Cp)_2MCl(OEt)$, $C_2H_4(Ind)_2M(NMe_2)_2$, $C_2H_4(Me_4Cp)_2MCl_2$, $C_2Me_4(Ind)_2MCl_2$, $Me_2Si(3-Me-Ind)_2MCl_2$, $C_2H_4(2-Me-Ind)_2MCl_2$, $C_2H_4(3-Me-Ind)_2MCl_2$, $C_2H_4(4,7-Me_2-Ind)_2MCl_2$, $C_2H_4(5,6-Me_2-Ind)_2MCl_2$, $C_2H_4(2,4,7-Me_3Ind)_2MCl_2$, $C_2H_4(3,4,7-Me_3Ind)_2MCl_2$, $C_2H_4(2-Me-H_4Ind)_2MCl_2$, $C_2H_4(4,7-Me_2-H_4Ind)_2MCl_2$, $C_2H_4(2,4,7-Me_3-H_4Ind)_2MCl_2$, $Me_2Si(4,7-Me_2-Ind)_2MCl_2$, $Me_2Si(5,6-Me_2-Ind)_2MCl_2$, $Me_2Si(2,4,7-Me_3-H_4Ind)_2MCl_2$.

12. Process according to Claim 1, in which the catalyst used in the first stage of polymerization (A) comprises the product of the reaction between an alkyl-Al compound, an electron-donor compound (external donor) and a solid component comprising at least one compound of a transition metal M^I selected from Ti and V and not containing $M^I-\pi$ bonds, a magnesium halide in active form and an electron-donor compound (internal donor).
13. Process according to Claim 12 in which the electron-donor compound (external donor) is selected from the group consisting of compounds of Si of the formula $R_1R_2Si(OR)_2$ in which R_1 and R_2 , which may be equal or different, are alkyl, cycloalkyl or aryl groups with from 1 to 18 carbon atoms and R is an alkyl radical with from 1 to 4 carbon atoms.
14. Process according to Claim 1, in which the compound capable of deactivating the catalyst used in stage (A) is selected from the group consisting of: CO, COS, CS_2 , CO_2 , O_2 , acetylenic compounds, allenic compounds and compounds of the general formula $R_{y-1}XH$ in which R is hydrogen or a hydrocarbon group with from 1 to 10 carbon atoms, X is O, N or S, and y is the valency of X.
15. Process according to Claim 1 in which the compound capable of deactivating the catalyst present in stage (A) is water.
16. Process according to Claim 1 in which, in stage (B), the product obtained in the first stage of polymerization (A) is:
 - (a) brought into contact with aliphatic hydrocarbons containing, in solution, suspension or dispersion, quantities of deactivating compound such that the molar

ratio of such compound to M^I is greater than 50; and,

(b) treated with solutions containing the compound of the transition metal M and an alkyl-Al compound selected from the Al trialkyls in which the alkyl groups have from 1 to 12 carbon atoms, and linear or cyclic aluminosiloxane compounds containing the repeat unit $-(R_4)AlO-$ in which R_4 is an alkyl group with 1-12 carbon atoms or a cycloalkyl or aryl group with 6-10 carbon atoms, said aluminosiloxane compounds containing from 1 to 50 repeat units.

17. Process according to Claim 1, in which, during the polymerization stage (C), at least one reactor is loaded with the product obtained in treatment stage (B) and, together or separately, with an alkyl-Al compound selected from the Al trialkyls in which the alkyl groups have from 1 to 12 carbon atoms, and linear or cyclic aluminosiloxane compounds containing the repeat unit $-(R_4)AlO-$ in which R_4 is an alkyl group with 1-12 carbon atoms or a cycloalkyl or aryl group with 6-10 carbon atoms, the said aluminosiloxane compounds containing from 1 to 50 repeating units.
18. Process according to Claim 1, in which, the polymerization stage (A) is carried out in the liquid phase, the said liquid phase being constituted of a hydrocarbon solvent or of one or more olefins $CH_2=CHR$ and in which, the polymerization stage (C) is carried out in at least one gas-phase reactor with a fluidized bed or a mechanically stirred bed.
19. Process according to Claim 1, in which, in both stages (A) and (C), polymerization is carried out working in gas-phase

reactors with a fluidized bed or a mechanically-stirred bed.

20. Process according to Claim 1 in which, the treatment stage (B) is carried out in a gas-phase loop reactor.
21. Process according to Claim 1, in which the amount of polymer produced in stage (A) is between 10 and 90% by weight based on the total amount of polymer produced in stages (A) and (C).
22. Process according to Claim 1, in which the amount of polymer produced in stage (A) is between 20 and 80% by weight relative to the total amount of polymer produced in stages (A) and (C).
23. Multistage process for the preparation of heterophase copolymers of propylene, characterized in that it comprises:
 - (A) a first stage of polymerization in which, in one or more reactors, propylene and possibly ethylene and/or one or more olefins $\text{CH}_2=\text{CHR}^{\text{II}}$, where R^{II} is a hydrocarbon radical with 2-10 carbon atoms, are polymerized in the presence of a catalyst comprising the product of the reaction between an alkyl-Al compound, optionally an electron-donor compound (external donor) and a solid component comprising at least one compound of a transition metal M^{I} selected from titanium and vanadium and not containing $\text{M}^{\text{I}}-\pi$ bonds, a magnesium halide in active form and optionally an electron-donor compound (internal donor), obtaining an olefin polymer having porosity, expressed as percentage of voids, greater than 10%, content of units derived from ethylene and/or from the $\text{CH}_2=\text{CHR}^{\text{II}}$ olefin less than 20% by weight, content of units derived from propylene

greater than 80% by weight and insolubility in xylene greater than 60%;

(B) a treatment stage in which the product obtained in stage (A) is, in any order whatever:

(a) brought into contact with a compound that is capable of deactivating the catalyst present in stage (A);

(b) brought into contact with a compound of a transition metal M selected from Ti, V, Zr and Hf containing at least one M- π bond and possibly with an alkyl-Al compound;

(C) a second stage of polymerization in which, in one or more reactors, one or more olefins $\text{CH}_2=\text{CHR}$, where R is hydrogen or an alkyl, cycloalkyl or aryl radical with 1-10 carbon atoms, are polymerized in the presence of the product obtained in stage (B), obtaining a substantially amorphous olefin (co)polymer in a quantity of between 20 and 80% by weight based on the total amount of polymer produced in stages (A) and (C).

24. Olefin homo or copolymers obtained by a process according to claim 1 or 23.

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C08F297/08 C08F2/42 C08F4/642 C08F4/654

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	EP,A,0 433 990 (HOECHST AG) 26 June 1991 cited in the application see the whole document ---	1-24
Y	EP,A,0 558 987 (BASF AG) 8 September 1993 see claims; example 1 ---	1-24
A	WO,A,94 17112 (DOW CHEMICAL CO) 4 August 1994 see page 4, line 24 - page 5, line 18; claims 12-22 ---	1,23,24
A	EP,A,0 174 863 (MITSUI PETROCHEMICAL IND) 19 March 1986 see claims; examples -----	1

☐ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
- "&" document member of the same patent family

Date of the actual completion of the international search

30 January 1996

Date of mailing of the international search report

12.02.96

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Kaumann, E

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-0433990	26-06-91	DE-A- 3942364	27-06-91
		AU-B- 647433	24-03-94
		AU-B- 6830190	27-06-91
		CA-A- 2032803	22-06-91
		DE-D- 59008936	24-05-95
		ES-T- 2072361	16-07-95
		JP-A- 6206921	26-07-94
		US-A- 5280074	18-01-94

EP-A-0558987	08-09-93	DE-A- 4206367	02-09-93
		JP-A- 5287024	02-11-93

WO-A-9417112	04-08-94	AU-B- 6267094	15-08-94
		CA-A- 2153978	04-08-94
		CN-A- 1090856	17-08-94
		EP-A- 0681592	15-11-95
		FI-A- 953626	28-07-95
		NO-A- 952995	28-09-95

EP-A-0174863	19-03-86	JP-C- 1504852	13-07-89
		JP-A- 61069822	10-04-86
		JP-B- 63054296	27-10-88
		JP-C- 1668494	29-05-92
		JP-A- 61069821	10-04-86
		JP-B- 63054294	27-10-88
		CA-A- 1235543	19-04-88
		US-A- 4739015	19-04-88